

PRODUCT NAME

# Nano-Gard 100 ST™

## Waterproofing, water borne silicate based concrete sealer



MANUFACTURER

Gemite® Products Inc.

Toll Free: 888-4-GEMITE (888-443-6483)

E-mail: [techinfo@gemite.com](mailto:techinfo@gemite.com)

Web Site: [www.gemite.com](http://www.gemite.com)

USA

160-3480 East Robinson Rd.

Amherst, NY 14228

Phone 888-443-6483

Fax 888-443-6329

CANADA

1787 Drew Road

Mississauga, Ontario L5S 1J5

Phone 905-672-2020

Fax 905-672-6780

FEATURES AND BENEFITS

- water borne
- penetrating
- chemically reactive with the substrate
- hardens and waterproofs concrete surface
- breathable
- protects against penetration of water and salts
- chemically resistant to oils, gasoline and hydraulic fluids
- increases chemical resistance of concrete

PRODUCT DESCRIPTION

Basic Use

*Nano-Gard 100 ST* is a clear, water borne penetrating sealer, which is used for dustproofing, hardening, moisture and oil proofing of concrete walls, floors, parking garage slabs, walks and driveways. It is mixed with water in ratios varying from 1.5 to 2.5 volume parts of water to 1 volume part of *Nano-Gard 100 ST*. For maximum penetration, the dilution ratio is typically 1 volume part of *Nano-Gard 100 ST* to 2 volume parts of potable water. For positive or negative side waterproofing on walls and slabs it is followed by application of hydrophobic *Nano-Gard 100 Plus*. The larger dynamic cracks must be treated separately. Please contact Gemite Technical Service for further information.

Composition of Materials

*Nano-Gard 100 ST* contains water borne silicate solutions and wetting agents. When properly diluted with water, it penetrates through the capillary pores of concrete and chemically reacts with products of hydration, filling the open pores and closing small voids.

Limitations

*Nano-Gard 100 ST* does not provide water or oil repellence. It may cause a slight darkening of the substrate in some instances. Prepare a site test sample for approval by client/architect if the possibility of darkening is of concern. The water repellence can be achieved by using *Nano-Gard 100 Plus* in the last coat. The larger dynamic cracks must be treated separately. Please contact Gemite Technical Service for further information.

Health and Safety

*Nano-Gard 100 ST* is nontoxic and nonflammable. Do not take internally; keep out of reach of children. Depending on the degree of alkalinity, (the dilution ratio with water), *Nano-Gard 100 ST* may irritate or burn the skin and eyes. If contact with skin occurs, wash with soap and water. Harmful if digested. Keep the product out of reach of children. FOR INDUSTRIAL USE ONLY. It is non-hazardous for transportation purposes. Consult MSDS for additional information.

Packaging

*Nano-Gard 100 ST* is supplied 20 L (5 USG) containers, or 209 L ( 55.3 USG drums).

Coverage

For treating concrete walls or slabs *Nano-Gard 100 ST* is typically mixed with water in volume ratio of 1:2 (One volume part of *Nano-Gard 100 ST* and two volume parts of water) When mixed with water 1: 2, the typical coverage is 3.7- 4.9 m<sup>2</sup> per L (150-200 ft<sup>2</sup> per USG), per one coat of the diluted solution. Typically two coats are applied. For waterproofing or chloride arresting purposes apply in the second or third coat the hydrophobic *Nano-Gard 100 Plus*. The above figures are for estimation purposes only. The coverage rate must satisfy the substrate porosity, but do not overapply - formation of white latencies on the surface is an indication of excess amount being applied.

TECHNICAL DATA

Weight:	1.18 kg/L, 9.82 lbs/USG
Penetration	3 to 6 mm (1/8 - 1/4 in )
Appearance	Liquid
Color	Clear to hazy white
Odor	Odorless
pH	11- 12
Solubility in water	Miscible

Storage and Transportation

Shelf life of unopened containers is 4 years.

INSTALLATION

Surface must be clean and free of dust, dirt, oil and other contaminants. The surface to be treated must be dry to allow good penetration of *Nano-Gard 100 ST*. All caulking, patching and joint sealing must be installed prior to application of *Nano-Gard 100 ST*. Existing larger dynamic cracks and junction between horizontal slab and wall need to be treated (waterproofed) separately. There are different methods of treating these types of cracks, depending on the type of application. Contact Gemite Technical Service for further information.. *Nano-Gard 100 ST* will not waterproof these. Clean the surface

Gemite Products Inc.  
October 2011

3 & 7

03064 Concrete Sealers  
03055 Concrete Surface Hardeners

well - a light shotblast or a high pressure water wash 5,000 psi (34 MPa). Dry the surface over night or longer, to get completely dry substrate. The typical application may proceed as follows: Apply the 1<sup>st</sup> coat of *Nano-Gard 100 ST* mixed with water 1: 2, using a mop, broom or a squeegee and let it dry for 24 hours on horizontal surfaces. Use a low pressure sprayer on vertical (wall) surfaces. Apply the 2<sup>nd</sup> coat at the same dilution and let dry for 24 hours and pressure wash the surface with water to remove any excess material to avoid a possibility of white surface laitence. In waterproofing applications use in the 2<sup>nd</sup> or 3<sup>rd</sup> coat (if used) the hydrophobic *Nano-Gard 100 Plus*. Keep in mind, that after application of hydrophobic *Nano-Gard 100 Plus*, an additional water borne coats (or paints) can't be applied, since the surface will be rendered hydrophobic. Note: The use of *Nano-Gard 100 ST* for hardening concrete floors and rendering them resistant to the formation of dust under tracking operations depends for its success not so much on the silicate film left on the surface as on the siliceous deposit which closes the pores. For this reason it is the best to choose a dilution just sufficient to permit the whole liquid applied to the surface to be absorbed into the concrete and then to use a somewhat stronger solution for later applications, thus gaining the advantage in the first instance of strengthening the wear resistance and in the second of securing the surface against the penetration of oils and other liquids. Fresh concrete contains free lime, which will slowly react with the penetrating solution to form an insoluble gel, which increases the resistance to wear and penetration of liquids. The appropriate *Nano-Gard 100 ST* concentration will vary with porosity of the concrete. Leave 24 hours between applications. Use potable water for dilution, providing that a cloudish precipitate does not appear after mixing *Nano-Gard 100 ST* with water. Otherwise, use de-ionized water.

## **MAINTENANCE**

No maintenance required.

## **WARRANTY**

A limited, twelve (12) months, Material Replacement Warranty is available. Contact Gemite Technical Service for further information.

## **TECHNICAL SERVICE**

For advice on suitability of *Nano-Gard 100 ST* for a specific application, specification assistance and application advice contact Technical Services: US (888) 443-6483 or Canada (905) 672-2020.

## **Short Specification**

The penetrating sealer will be water borne silicate based *Nano-Gard ST 100*, manufactured by Gemite Products Inc., Amherst, NY (Mississauga, Ontario). It shall be applied at a minimum rate of \_\_\_\_\_m<sup>2</sup>/L ( ft<sup>2</sup> )/USG and dilutions as per manufacturer's current Guide Specifications and Application Instructions.